## FIBERFRAX DURABOARD 1500 & 1600

## **Description**

Fiberfrax Duraboard products are manufactured from Fiberfrax refractory ceramic fibres, blended with specially selected inorganic and organic binders to give rigid boards with exceptional characteristics. Fiberfrax Duraboard 1500 & 1600 are produced from a blend of Fiberfrax and high alumina polycrystalline fibres. This combination increases the continuous operating temperature capability, provides very low shrinkage at elevated temperatures, whilst maintaining excellent insulating properties. Fiberfrax Duraboard products are available in a wide range of sizes and thicknesses



#### **General characteristics**

Fiberfrax Duraboard has these outstanding characteristics:

- High temperature stability
- Low thermal conductivity
- Resistance to thermal shock
- Resistance to erosion
- Easy to cut with standard tools
- Low warpage

ш

ш

ш

## **Typical applications**

- High temperature furnace and kiln linings
- Rigid high temperature gaskets and seals
- Heat shields
- Gas boiler combustions chamber linings

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

	Duraboard 1500	Duraboard 1600
Typical Chemical Analysis (fibre wt. %)		
SiO <sub>2</sub>	44.0 - 50.0	37.0 - 43.0
$AI_2O_3$	49.0 - 55.0	56.0 - 62.0
$Fe_2O_3 + TiO_2$	<0.5	<0.5
Alkalis	<0.25	<0.25
Physical Properties		
Colour	White / Tan	White / Tan
Product Density (kg/m3)	230	200
Modulus of Rupture (kPa)	>500	>400
Use Limit (°C) *	1500	1600
Loss on Ignition (wt.%)	<7.0	<7.0
Thermal Conductivity (W/mK) Mean Temp.		
1000 °C	0.16	0.18
1200 °C	0.20	0.24
1400 °C	0.26	0.36
Permanent Linear Shrinkage (%) 24 hour soak	(	
1500 °C	<4.0	-
1600 °C	-	<4.0

Insulcon B.V.- The Netherlands - Tel: +31 (0) 167 565750 Insulcon GmbH - Germany - Tel: +49 (0) 2131 408548-0 Insulcon N.V. - Belgium - Tel: +32 (0) 3 711 02 78 Insulcon Projects S.A. - Switzerland - Tel: +41 (0) 91911739-0



Form: A1-141 Effective: 03012022/ES Supersedes: 21042010/ES/ka All rights Reserved

## FIBERFRAX DURABOARD 1500 & 1600

**Availability** 

rttanasmty								
Thickness	1500	1600	Sheet	Quantity	Loose	Sheet	Quantity	Loose
			dimensions	sheets per	sheets	dimensions	sheets per	sheets per
			(mm)	carton	per	(mm)	carton	pallet
					pallet			
10 mm			610 x 1000	10	220	1250 x 1000	10	110
12 mm			610 x 1000	8	176	1250 x 1000	8	88
18 mm			610 x 1000	5	110	1250 x 1000	5	55
25 mm			610 x 1000	4	88	1250 x 1000	4	44
50 mm			610 x 1000	2	44	1250 x 1000	2	22

Other thicknesses/sizes may be available on request subject to minimum order requirements.

# **Handling information**

区

Ш

Ш

Ш

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Insulcon B.V.- The Netherlands - Tel: +31 (0) 167 565750 Insulcon GmbH - Germany - Tel: +49 (0) 2131 408548-0 Insulcon N.V. - Belgium - Tel: +32 (0) 3 711 02 78 Insulcon Projects S.A. - Switzerland - Tel: +41 (0) 91911739-0



Form: A1-141 Effective: 03012022/ES Supersedes: 21042010/ES/ka All rights Reserved